

Product Specifications	Standard	Rolls & Tiles	Raised Access Floor Tiles (Square and Plank)
<b>Composition</b>	-	87% vinyl + 13% polyester + backing 100% vinyl	87% vinyl + % polyester + backing 100% vinyl
<b>Weight (g/m<sup>2</sup>) (oz/sq ft)</b>	ISO 8543:1998	3500 g/m <sup>2</sup> (11.5 oz/sq ft) +13% / -10%	4275 g/m <sup>2</sup> (14.0 oz/sq ft) +13% / -10%
<b>Thickness (mm.) (in)</b>	ISO 1765:1986	2.60 mm (0.10 in)	3.30 mm (0.13 in)
<b>Light Fastness (Grey scale: 1-5)</b>	EN ISO 4892:2006 (exterior)	>4/5	>4/5
<b>Light Fastness (Blue scale: 1-8)</b>	EN ISO 105B02:2001 (interior)	>7/8	>7/8
<b>Dimensional Stability %</b>	EN ISO 23999:2012	≤0.25%	≤0.25%
<b>Residual Indentation</b>	EN ISO 24343-1:2012	<0.10 mm (<0.003 in)	<0.10 mm (<0.003 in)
<b>Castor Chair Test</b>	EN 985:2002	Intensive use	Intensive use
<b>Sound Insulation</b>	EN ISO 10140-3:2011	14 dB	15 dB
<b>Thermal Resistance</b>	EN 12667:2001	< 0.15m <sup>2</sup> K/W	< 0.15m <sup>2</sup> K/W
<b>Static Electricity</b>	EN 1815:1997	< 2 kV	< 2 kV
<b>Slip Resistance</b>	EN 13893:2003	>0.4	>0.4
<b>Slip Resistance</b>	DIN 51130:2014 DIN 5097:1992	R9 Class C	R9 Class C
<b>Slip Resistance</b>	ASTM C1028-96 Static Coefficient	Wet: 0.62; Dry: 0.70	Wet: 0.62; Dry: 0.70
<b>Slip Resistance</b>	BS 7976-2:2002 Pendulum Test	Wet: 41; Dry: 52	Wet: 41; Dry: 52
<b>Fire Classification</b>	EN 13501-1:2007	Bfl-S1	Bfl-S1
<b>Fire Classification</b>	ASTM E648 (NFPA 253)	Class 1	Class 1
<b>Antibacterial activity</b>	ASTM E 2180-07(2012) ASTM G21:2013	Inhibition of bacterial growth & Antifungal activity	Inhibition of bacterial growth & Antifungal activity
<b>Roll Width</b>	-	200 cm 78.740 in	
<b>Roll Length</b>	-	10 lm (32.81 ft) 20 lm (65.62 ft)	
<b>CE Certificate</b>	EN 14041:2004	0338-CPR-2002	0338-CPR-2002
<b>Use Classification</b>	EN 1307:2014	Heavy Commercial	

<b>Tile Dimensions</b>	Square	Plank	Diamond	Hexagon	E. Triangle	I. Triangle
	a = 50cm / 19 11/16 in	a = 75cm / 29 1/2 in b = 25cm / 9 13/16 in	a = 50cm / 19 11/16 in b = 50cm / 19 11/16 in	a = 54cm / 21 1/4 in b = 61.4cm / 24 3/16 in L = 30.7cm / 12 1/16 in	a = 50cm / 19 11/16 in	a = 50cm / 19 11/16 in Z = 70.7cm / 27 13/16 in

All specifications are based on average values and may deviate. The values are for guidance and not contractual. Subject to technical modifications. The straight weft is not an inherent condition. Weaving technology features colour effects because of light, making it an exclusive and unique product. Also bicolour yarns create a randomly harmonious effect. These effects are no ground for claims.